

CORRECTED VERSION

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
5 February 2004 (05.02.2004)

PCT

(10) International Publication Number
WO 2004/011724 A1

(51) International Patent Classification⁷: E01C 13/08,
13/02

GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC,
SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA,
UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(21) International Application Number:
PCT/NL2003/000542

(22) International Filing Date: 24 July 2003 (24.07.2003)

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(25) Filing Language: Dutch

(26) Publication Language: English

(30) Priority Data:
1021171 29 July 2002 (29.07.2002) NL

Published:

— with international search report

(71) Applicants and

(72) Inventors: DE VRIES, Hugo [NL/NL]; Ringdijk 430,
NL-2983 GS Ridderkerk (NL). ROOK, Pieter [NL/NL];
Randweg 27, NL-2983 AL Ridderkerk (NL).

(48) Date of publication of this corrected version:

31 March 2005

(74) Agent: BARTELD, Erik; Arnold & Siedsma, Sweel-
inckplein 1, NL-2517 GK The Hague (NL).


(15) Information about Correction:

see PCT Gazette No. 13/2005 of 31 March 2005, Section II

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: METHOD FOR LAYING A PASSABLE SURFACE, FOR INSTANCE A PLAYING GROUND, AND SURFACE THUS FORMED



(57) Abstract: The invention relates to a method for laying a playable surface such as a playing field, comprising the steps of forming a hard substrate, arranging on the hard substrate a layer of resilient and/or damping material, and arranging a top layer on the resilient and/or damping layer, wherein during or after arranging of the hard substrate and/or the resilient and/or damping layer air chambers are formed therein. The behaviour of the playing field becomes more natural due to these air chambers, and excessive resilience and energy restitution are avoided. The air chambers can be formed for instance by creating recesses in the relevant layer from the top, or by removing material from the layer at different locations after arranging thereof, for instance by melting or biological decomposition of inclusions. The invention also relates to a playing field obtain by application of this method.

BEST AVAILABLE COPY

WO 2004/011724 A1

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
5 February 2004 (05.02.2004)

PCT

(10) International Publication Number
WO 2004/011724 A1

(51) International Patent Classification⁷: **E01C 13/08**,
13/02

(21) International Application Number:
PCT/NL2003/000542

(22) International Filing Date: 24 July 2003 (24.07.2003)

(25) Filing Language: Dutch

(26) Publication Language: English

(3^a) Priority Data:
1021171 29 July 2002 (29.07.2002) NL

(71) Applicant and

(72) Inventor: **DE VRIES, Hugo** [NL/NL]; Ringdijk 430,
NL-2983 GS Ridderkerk (NL).

(71) Applicant and

(72) Inventor (*for US only*): **ROOK, Pieter** [NL/NL];
Randweg 27, NL-2983 AL Ridderkerk (NL).

(74) Agent: **BARTELD, Erik**; Arnold & Siedsma, Sweet-
inckplein 1, NL-2517 GK The Hague (NL).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METHOD FOR LAYING A PASSABLE SURFACE, FOR INSTANCE A PLAYING GROUND, AND SURFACE THUS FORMED



(57) Abstract: The invention relates to a method for laying a playable surface such as a playing field, comprising the steps of forming a hard substrate, arranging on the hard substrate a layer of resilient and/or damping material, and arranging a top layer on the resilient and/or damping layer, wherein during or after arranging of the hard substrate and/or the resilient and/or damping layer air chambers are formed therein. The behaviour of the playing field becomes more natural due to these air chambers, and excessive resilience and energy restitution are avoided. The air chambers can be formed for instance by creating recesses in the relevant layer from the top, or by removing material from the layer at different locations after arranging thereof, for instance by melting or biological decomposition of inclusions. The invention also relates to a playing field obtain by application of this method.

WO 2004/011724 A1

2 / PRTS

15 Rec'd PCT/PTO 13 JAN 2005

WO 2004/011724

PCT/NL2003/000542

1

METHOD FOR LAYING A PLAYABLE SURFACE, FOR INSTANCE A PLAYING
FIELD, AND SURFACE THUS FORMED

The invention relates to a method for laying a
playable surface, in particular a playing field, comprising
the steps of:

- forming a relatively hard substrate,
- 5 arranging on the relatively hard substrate at least
one layer of a resilient and/or damping material, and
- arranging a top layer on the at least one layer of
resilient and/or damping material. Such a method is generally
known and is applied on large scale to form playing fields,
10 for instance synthetic turf fields for sport and recreation.
Synthetic turf fields are used particularly for playing ball
sports such as football, American football, hockey and the
like.

- In accordance with the known method a surface such
- 15 as a synthetic turf field is formed by first forming a
relatively hard, flat substrate, for instance an asphalt
layer, on the ground. A resilient and/or damping layer must
then be arranged over this asphalt layer, because the field
would otherwise be too hard to play on, and would result in
20 injuries to players. This resilient and/or damping layer can
be arranged in the form of a mixture consisting of plastic or
rubber granules or particles which are held together by a
binder, or in the form of solid material supplied on rolls,
for instance a closed or open-cell foam. The resilient and/or
25 damping material is arranged or unrolled on-site on the
substrate, whereafter it is covered by the top layer, for
instance a synthetic turf.

The known method has the drawback that the thereby

WO 2004/011724

PCT/NL2003/000542

2

formed playing field is often perceived as being too "bouncy" and has too great an energy restitution. The behaviour of a ball is adversely affected by the large spring force of the resilient layer in the sense that a ball bounces too fast and too high compared to a natural turf. In addition, walking or running over such a resilient synthetic turf field is very tiring and unnatural.

The invention therefore has for its object to provide a method which results in a playing field, in particular a synthetic turf field, which more closely resembles a natural turf field than the synthetic turf fields laid heretofore, which enables a better ball behaviour and which does not result in excessive fatigue when playing on the field. According to the invention this is achieved in a method of the above described type in that, during or after arranging of the relatively hard substrate and/or the layer of resilient and/or damping material, air chambers are formed therein. As a result of the air chambers in the layer of resilient and/or damping material, or even in the relatively hard substrate, movements on the synthetic turf field are damped. Balls for instance hereby do not bounce too high, and walking or running over the synthetic turf also feels natural. By further forming the air chambers during or after laying of the resilient and/or damping layer or the hard substrate, these layers do not need to be manufactured from specially preprocessed material, and relatively simple, and therefore not very costly materials can be used for this purpose.

A preferably applied variant of the method consists of the air chambers being formed in the relatively hard substrate and/or the layer of resilient and/or damping material by creating recesses therein from the top side after it is arranged. The arranging of recesses from the top can be

WO 2004/011724

PCT/NL2003/000542

3

carried out quickly and with relatively simple means. The recesses are preferably created by moving a machine provided with protruding parts over the relatively hard substrate and/or the layer of resilient and/or damping material. By using for instance a pressure roller provided with studs as machine, the recesses can be formed simultaneously with pressing down of the substrate or resilient and/or damping layer, whereby no additional operation is necessary.

10 In addition, it is also possible to create the recesses by pressing a profiled mat into the layer of resilient and/or damping material. A mat is here understood to mean any relatively thin closed material, for instance a woven fabric, a non-woven, a foil and the like. A simple, smooth roller can in this case be used.

15 It is on the other hand also possible to envisage the air chambers being formed in the layer of resilient and/or damping material by removing material therefrom at different locations after the arranging thereof. A simple method of forming the required air chambers in precisely controlled manner consists of inclusions of a material with low melting point being arranged in the layer of resilient and/or damping material which are removed by heating after the layer has been arranged. According to a variant, inclusions of a biologically degradable material are arranged in the layer of resilient and/or damping material which are removed by natural processes after the layer has been arranged. In this manner the air chambers are created automatically after a period of time without any operations being necessary for this purpose.

30 According to yet another variant of the method according to the invention, the air chambers are formed in the layer of resilient and/or damping material during arranging thereof by including granules having large

WO 2004/011724

PCT/NL2003/000542

4

dimensions relative to the thickness of the layer. The air chambers can thus be formed by replacing a part of the resilient and/or damping material with material of a considerably larger size, whereby the degree to which the resilient and/or damping layer is filled will decrease greatly as a result of the poorer fit of the large granules, without additional operations being necessary for this purpose. In that case the layer of resilient and/or damping material can for instance be arranged in two steps, by first arranging a relatively flat adhesive layer of material on the relatively hard substrate, and subsequently spreading the granules with large dimensions over the adhesive layer.

Finally, it is also conceivable for the air chambers to be formed in the layer of resilient and/or damping material during arranging thereof by first laying a profiled mat on the relatively hard substrate, and by spreading the resilient and/or damping material over this mat. Such a profiled mat in fact already contains the air chambers, so that the resilient and/or damping material need only be placed thereover and spread to form a layer which is flat on the upper side. Prior to arranging of the mat, heating wires can advantageously be received therein, so that the mat can also serve as ground heating.

In the case use is made of a profiled mat, this mat can otherwise be manufactured from a biologically degradable material or from a material with a low melting point. After forming of the playing field the mat can thus decompose in natural manner or be removed by heating.

In order to nevertheless form a very flat upper layer on which the synthetic turf can be laid, this despite the presence of the air chambers, at least one other layer can also be arranged between the layer with the air chambers and the synthetic turf. This layer can for instance serve to

WO 2004/011724

PCT/NL2003/000542

5

distribute the load on the top layer uniformly into the substrates, or can serve for additional resilience and/or damping.

When a synthetic turf is placed as top layer, a
5 synthetic turf field is formed with the method according to the invention which has a very natural feel.

At least some of the air chambers are advantageously connected to means for generating an air circulation therein. Warm air for instance can thus be blown
10 under the playing field, whereby a simple and effective ground heating is obtained.

The invention further relates to a playable surface, in particular a playing field, comprising a relatively hard substrate, at least one layer arranged
15 thereon of a resilient and/or damping material, and a top layer arranged in turn thereon. Such a surface, for instance in the form of a synthetic turf field, is likewise generally known, and has the above discussed drawbacks.

The invention has for its object to further improve
20 a playable surface of the stated type. According to the invention this is achieved in such a surface by air chambers formed in the relatively hard substrate and/or the layer of resilient and/or damping material.

Preferred embodiments of the playable surface
25 according to the invention are described in the dependent claims 16 to 23.

The invention is now elucidated on the basis of a number of embodiments, wherein reference is made to the annexed drawing, in which:

30 Fig. 1 is a schematic cross-section showing the structure of a prior art playing field, and

Fig. 2 to 6 show corresponding cross-sections through different embodiments of the playing field according

WO 2004/011724

PCT/NL2003/000542

6

to the invention.

A playable surface, for instance a prior art synthetic turf field 1 (fig. 1) is formed by a relatively hard substrate 2, for instance of asphalt or stone chippings, over which a flat layer of resilient and/or damping material 3 is arranged. This resilient and/or damping layer 3 can have a thickness of about 10 to 40 mm. Arranged on the resilient and/or damping layer 3 is a top layer 4, here in the form of a synthetic turf consisting of a backing 5 and synthetic grass blades 6 connected thereto by tufting, knitting or weaving.

The resilient and/or damping layer 3 can be formed in different ways. It is for instance known to use a mixture of rubber granules 8 with relatively small dimensions, in the order of several millimetres, for instance 2-5 mm, which are mixed with a liquid binder, for instance polyurethane. The thus formed mixture can then be spread over substrate 2 using an asphaltting machine or a paver specially developed for the purpose. It is also possible on the other hand to use as resilient and/or damping material 3 a foam material which is supplied on rolls and simply unrolled over the hard substrate 2.

As already indicated above, the known synthetic turf field 1 is exceptionally "bouncy" as a consequence of the presence of the layer of resilient and/or damping material 3, whereby in the case of ball games the bouncing behaviour of the ball is affected, which does not generally enhance the quality of the game. The excessive resilience and energy restitution of the synthetic turf field is moreover perceived by players as being unpleasant and tiring.

So as to obviate these problems, it is proposed according to the invention to form air chambers in the layer of resilient and/or damping material 3 or between the layer

WO 2004/011724

PCT/NL2003/000542

7

of resilient and/or damping material 3 and the relatively hard substrate 2.

According to a first variant of the invention, the air chambers 17 are formed in the upper part of the layer of resilient and/or damping material 13 (fig. 2). For this purpose recesses are formed from the top in the resilient and/or damping layer 13. These recesses can take a random form, for instance be of circular cross-section. They are preferably distributed uniformly over the surface of the synthetic turf field 11. When the resilient and/or damping layer 13 consists of a mixture of rubber granules 18 and a binder, the recesses can be formed after the resilient and/or damping layer 13 has been arranged on the relatively hard substrate 12, but before it has hardened. A machine provided with protruding parts (not shown here) can for instance be moved for this purpose over the not yet hardened resilient layer 13. A profiled pressure roller can be envisaged here, whereby the recesses that will define the air chambers 17 are thus formed directly during pressing down of the resilient and/or damping layer 13. In this manner the forming of air chambers 17 does not require a separate operating run.

According to a variant of this method, air chambers 17 are formed by laying a profiled mat 20 on the resilient and/or damping layer 13 before this latter hardens, and by then pressing this mat 20 into the resilient and/or damping layer 13 (fig. 3). Use can herein then be made of a standard roller or pressure roller without profile. Mat 20 can form a permanent part of the substrates, but could also be removed during curing of the resilient and/or damping layer. The mat could be manufactured for this purpose from a material with low melting point, and could therefore be easily removed by heating. The use of a biologically degradable material for mat 20 can also be envisaged.

WO 2004/011724

PCT/NL2003/000542

8

In the shown embodiment another layer 19 is otherwise also arranged between the resilient and/or damping layer 13 and top layer 14, here in the form of a pressure distribution layer of a relatively stiff material, whereby the loads on top layer 14 are distributed evenly over the resilient and/or damping layer 13, and subsidence of top layer 14 at the position of air chambers 17 is prevented. A second flat resilient and/or damping layer could however also be arranged instead of a pressure distribution layer 19.

Heating wires of a conductive material could further be included in mat 20 or in the additional layer 19, which wires could be connected to one or more electrical power supplies along the edge of the playing field. In this way the playing field 11 can be heated in simple manner, whereby it remains readily playable, also in winter.

When the layer of resilient and/or damping material 13 is a foam material supplied on rolls, the recesses for the air chambers could be formed by local processing, either mechanically, thermally or chemically, of the upper side of the resilient and/or damping layer 13.

It is also possible to envisage the resilient and/or damping layer 13 being formed by a mixture of rubber granules 18 and binder which incorporates inclusions of a material which can be easily removed from the resilient and/or damping layer 13 after arranging thereof. It is for instance possible to envisage inclusions of a material with a low melting point, such as polystyrene granules, which after arranging of the resilient and/or damping layer 13 can be removed by heating this layer to above the melting point of the inclusions. Another possibility is the use of inclusions of a biologically degradable material which will decompose automatically after a period of time, whereby air chambers are again formed in the resilient and/or damping layer 13.

WO 2004/011724

PCT/NL2003/000542

9

The inclusions can herein be distributed over the whole layer 13, though it is also possible to envisage them being concentrated close to the top side, so that after heating or after decomposition of the material a pattern is created as
5 according to fig. 2 and 3.

In another embodiment of the synthetic turf field 21 according to the invention (fig. 4) the air chambers 27 are formed by intermediate spaces between relatively large granules 31 in the resilient and/or damping material. In the
10 shown embodiment these granules 31 have dimensions which are almost the same as the thickness of the layer of resilient and/or damping material 23, although this is not always essential. For an optimal effect however, the granules 31 do have to have dimensions which are relatively large in
15 proportion to the thickness of the layer of resilient and/or damping material 23. It is possible to envisage dimensions amounting to more than half the thickness of the resilient and/or damping layer 23, preferably more than 70% thereof, and more preferably more than 85% thereof. The resilient
20 and/or damping layer 23 can be formed in this embodiment by first arranging on the relatively hard substrate 22 a relatively flat and thin adhesive layer 32 of resilient and/or damping material, consisting for instance of a mixture of relatively small granules 28 and binder or formed by a
25 compact layer of polyurethane, and then scattering the relatively large granules 31 in this adhesive layer 32. A synthetic turf 24 can then in turn be laid on the relatively large granules 31, wherein on the top side of the resilient and/or damping layer 23 intermediate spaces are thus created
30 which will function as air chambers 27. Also shown here is a pressure distribution layer 29 which, if desired, can be arranged between the resilient and/or damping layer 23 and top layer 24.

WO 2004/011724

PCT/NL2003/000542

10

According to yet another variant of the invention the air chambers are formed by first laying on the relatively hard substrate 42 a profiled, at least initially form-retaining mat 50, the profile of which, together with
5 substrate 42, defines air chambers 47 (fig. 5). Mat 50 can be a woven fabric with a mesh width smaller than the grain size of the resilient and/or damping material 48 which is spread over the profiled mat 50 and is finished to form a flat layer. A synthetic turf 44 can then be arranged thereover.
10 Heating wires can here also be incorporated in mat 50.

In yet another embodiment of synthetic turf field 51 according to the invention the air chambers 57 are likewise enclosed between the relatively hard substrate 52 and the resilient and/or damping layer 53, but are defined by
15 recesses in the relatively hard substrate 52, while the resilient and/or damping layer 53 is substantially flat. The recesses in the upper part of the relatively hard substrate 52 can be formed in the same manner as the recesses in the resilient and/or damping layer 13 according to the first
20 embodiment. A pressure distributing layer 59 can here optionally also be arranged between the relatively hard substrate 52 and the resilient and/or damping layer 53. A synthetic turf 54 is in turn laid on the flat layer of resilient and/or damping material 53, which in the shown
25 embodiment consists of a plastic foam.

Although not shown here, air chambers 17, 27, 47, 57 could be connected to means for generating an air circulation therein. These circulation means could be formed by one or more fans or compressors along the edge of the playing field
30 with which air could be blown through air chambers 17, 27, 47, 57. If this air is first heated, a simple system of ground heating is thus created.

The layer of resilient and/or damping material can,

WO 2004/011724

PCT/NL2003/000542

11

as stated, consist of a mixture of rubber granules and a binder such as polyurethane. In addition to the rubber granules, other plastic materials can also be used such as polystyrene granules, polyethylene foam, rubber foam, polyurethane foam and the like. In addition, use could be made in small part of stone chippings, thereby considerably reducing the cost of the resilient and/or damping layer.

Although the invention is elucidated above with reference to a number of embodiments, it will be apparent that it is not limited thereto, and that many modifications and adjustments are possible within the scope of the following claims. A further flat layer of resilient and/or damping material could for instance be arranged between the layer of resilient and/or damping material with the air chambers and the relatively hard substrate. In addition, the different variants of the layers with air chambers could be combined for an even better damping. The form and dimensions of the air chambers, their number and the distribution thereof over the playing field can further be varied as desired so as to arrive at the required degree of damping. Finally, other playing surfaces, such as floors of sports halls, athletic tracks and the like, can also be envisaged for application of the invention instead of synthetic turf fields. Even other types of surfaces suitable for walking on, such as floors in industrial premises or homes, could be provided with air chambers with the purpose of increasing comfort.

The scope of the invention is therefore defined solely by the claims.

Claims

1. Method for laying a playable surface, in particular a playing field, comprising the steps of:
forming a relatively hard substrate,
arranging on the relatively hard substrate at least
5 one layer of a resilient and/or damping material, and
arranging a top layer on the at least one layer of resilient and/or damping material,

characterized in that during or after arranging of the relatively hard substrate and/or the layer of resilient
10 and/or damping material air chambers are formed therein.

2. Method as claimed in claim 1, characterized in that the air chambers are formed in the relatively hard substrate and/or the layer of resilient and/or damping material by creating recesses therein from the top side after
15 it is arranged.

3. Method as claimed in claim 2, characterized in that the recesses are created by moving a machine provided with protruding parts over the relatively hard substrate and/or the layer of resilient and/or damping material.

20 4. Method as claimed in claim 2, characterized in that the recesses are created by pressing a profiled mat into the layer of resilient and/or damping material.

5. Method as claimed in claim 1, characterized in that the air chambers are formed in the layer of resilient
25 and/or damping material by removing material therefrom at different locations after the arranging thereof.

6. Method as claimed in claim 5, characterized in that inclusions of a material with low melting point are arranged in the layer of resilient and/or damping material
30 which are removed by heating after the layer has been arranged.

WO 2004/011724

PCT/NL2003/000542

13

7. Method as claimed in claim 5, **characterized in that** inclusions of a biologically degradable material are arranged in the layer of resilient and/or damping material which are removed by natural processes after the layer has
5 been arranged.

8. Method as claimed in claim 1, **characterized in that** the air chambers are formed in the layer of resilient and/or damping material during arranging thereof by including granules having large dimensions relative to the thickness of
10 the layer.

9. Method as claimed in claim 8, **characterized in that** the layer of resilient and/or damping material is arranged in two steps, by first arranging a relatively flat adhesive layer on the relatively hard substrate, and
15 subsequently spreading the granules with large dimensions over the adhesive layer.

10. Method as claimed in claim 1, **characterized in that** the air chambers are formed in the layer of resilient and/or damping material during arranging thereof by first
20 laying a profiled mat on the relatively hard substrate, and by spreading the resilient and/or damping material over this mat.

11. Method as claimed in claim 4 or 10, **characterized in that** prior to arranging of the mat heating
25 wires are received therein.

12. Method as claimed in any of the foregoing claims, **characterized in that** at least one other layer is also arranged between the layer with the air chambers and the
top layer.

30 13. Method as claimed in any of the foregoing claims, **characterized in that** the top layer is a synthetic turf.

14. Method as claimed in any of the foregoing

WO 2004/011724

PCT/NL2003/000542

14

claims, **characterized in that** at least some of the air chambers are connected to means for generating an air circulation therein.

15 15. Playable surface, in particular a playing field, comprising a relatively hard substrate, at least one layer arranged thereon of a resilient and/or damping material, and a top layer arranged in turn thereon, **characterized by** air chambers formed in the relatively hard substrate and/or the layer of resilient and/or damping material.

16. Surface as claimed in claim 15, **characterized in that** the air chambers take the form of recesses in the upper part of the relatively hard substrate and/or the layer of resilient and/or damping material.

15 17. Surface as claimed in claim 16, **characterized by** a profiled mat arranged on the layer of resilient and/or damping material, wherein the air chambers are defined by the profile of the mat.

20 18. Surface as claimed in claim 15, **characterized in that** the air chambers comprise spaces formed by removing inclusions in the layer of resilient and/or damping material.

25 19. Surface as claimed in claim 15, **characterized in that** the air chambers comprise intermediate spaces between relatively large granules in the layer of resilient and/or damping material.

30 20. Surface as claimed in claim 15, **characterized by** a profiled mat which is arranged between the relatively hard substrate and the layer of resilient and/or damping material and over which the resilient and/or damping material is spread, wherein the air chambers are defined by the profile of the mat.

21. Surface as claimed in claim 17 or 20, **characterized by** heating wires received in the mat.

WO 2004/011724

PCT/NL2003/000542

15




22. Surface as claimed in any of the claims 15-21,
characterized in that the top layer is a synthetic turf.




23. Surface as claimed in claims 15-22,
characterized by means connected to at least some of the air
5 chambers for generating an air circulation therein.

10/522795

WO 2004/011724

PCT/NL2003/000542





INTERNATIONAL SEARCH REPORT

Intern: Application No
PCT/NL 03/00542

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 E01C13/08 E01C13/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 E01C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 93 01356 A (PROFU AB) 21 January 1993 (1993-01-21) the whole document	1-3, 13-17, 20,22,23
X	US 5 254 039 A (GARCIA JUAN) 19 October 1993 (1993-10-19) the whole document	1,10, 13-17, 20,22,23 11,21
Y	US 4 007 307 A (FRIEDRICH HANS-JOACHIM) 8 February 1977 (1977-02-08) column 7, line 23 - line 27	11,21
X	DE 19 33 048 A (MINNESOTA MINING & MFG) 15 January 1970 (1970-01-15) claims 1,4	1,5,13, 15,18,22
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

20 October 2003

Date of mailing of the international search report

27/10/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Dijkstra, G.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/NL/03/00542

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 957 788 A (COLONEL RICHARD C ET AL) 18 September 1990 (1990-09-18) the whole document -----	1, 10, 12, 13, 15-17, 20, 22

INTERNATIONAL SEARCH REPORT

 Interna Application No
 PCT/NL 03/00542

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9301356	A	21-01-1993	SE 500700 C2	15-08-1994
			DE 69202461 D1	14-06-1995
			EP 0593650 A1	27-04-1994
			SE 9102133 A	09-01-1993
			WO 9301356 A1	21-01-1993
			US 5460867 A	24-10-1995
US 5254039	A	19-10-1993	NONE	
US 4007307	A	08-02-1977	DE 2051108 A1	20-04-1972
			AT 330046 B	10-06-1976
			AT 392374 A	15-08-1975
			AT 327062 B	12-01-1976
			AT 867671 A	15-03-1975
			BE 773722 A1	31-01-1972
			CH 534759 A	15-03-1973
			DK 128983 B	05-08-1974
			DK 142036 B	11-08-1980
			ES 396065 A1	01-05-1976
			FR 2111679 A1	09-06-1972
			GB 1320868 A	20-06-1973
			IT 939103 B	10-02-1973
			JP 51045894 B	06-12-1976
			MY 84287 A	31-12-1987
			NL 7114139 A ,B	19-04-1972
			NL 8103155 A ,B,	01-12-1981
			NO 133412 B	19-01-1976
			SE 373503 B	10-02-1975
DE 1933048	A	15-01-1970	CH 565575 A5	29-08-1975
			DE 1933048 A1	15-01-1970
			ES 368603 A1	16-10-1971
			FR 2011666 A5	06-03-1970
			GB 1277963 A	14-06-1972
			JP 53033635 B	14-09-1978
			SE 344544 B	24-04-1972
US 4957788	A	18-09-1990	US 3597297 A	03-08-1971
			US 5102703 A	07-04-1992

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.